

# TPY107 Quin Yellow Pigment for Automotive Applications



## TECHNICAL DATA SHEET

Technical Specifications	TPY107
Pigment Code	Pigment Yellow 138 (56300)
% Pigment	25%
Strength	100 +/- 2
DE	< 0.5
Weight Per Gallon (lbs)	8.9 +/- 0.2
Viscosity, #4 Spindle @ 20 RPM	3,000 +/- 2,000
Grind	7+

TPY107 demonstrates excellent color, opacity, and stability. It has been supplied to many of the major USA automotive PVC suppliers for more than 20 years.

### PACKAGING

55-Gallon Drum - 500 lbs

		Applications Performance														
		HDPE							PVC-p							
Full Shade	White Reduction	Migration FS 0.1%	Heat FS 0.1%	Heat WR 1:10	Light FS 0.1%	Light WR 1:10	Weather 3000 h FS 0.1%	Weather 3000 h WR 1:10	Warping	Migration FS 0.1%	Light FS 0.1%	Light WR 1:10	Hot light 600 kJ FS 0.1%	Hot light 600 kJ WR 1:10	Weather 5000 h FS 0.1%	Weather 5000 h WR 1:10
		4-5	280	270	8	7	-	-	L	4-5	7-8	7	5	4-5	-	-