

TUC1338R Crosslinker for Ultra-Clear High-Abrasion Topcoat

TECHNICAL DATA SHEET

Technical Specifications	TUC1338R
% Solids	15.0 +/- 2.0
Viscosity	8.0 +/- 2.0 seconds #3 Zahn
Weight per Gallon (lbs)	7.0 +/- 0.2
Grind	7+
Solvent System	Isopropyl Alcohol/Isobutanol

Preparation: TUC1354M2 - 84%; TUC1338R - 16%

Mix for 30 minutes, then adjust viscosity with a mixture of 80% Methyl Ethyl Ketone and 20% Isopropyl alcohol.

TUC1338R Crosslinker for Ultra-Clear High-Abrasion Topcoat is used in conjunction with TUC1354M2 for application in marine and automotive-convertible windows. The coating result is stable and does not need to be re-crosslinked over time. It will not gel or lose properties if the viscosity is maintained between 13-15 seconds #3 Zahn.

When finished with a run, drain the pan, adjust the viscosity and store the remainder in a sealed drum until needed again. Consult SOP's for handling instructions and recommended conditions of use.

PACKAGING

5-Gallon Plastic Pail = 35 lbs

