

# TUC1378 Crosslinker for Air Dry SRT

## TECHNICAL DATA SHEET

Technical Specifications	TUC1378
Viscosity	8.0 +/- 2.0 seconds #3 Zahn
Weight per Gallon (lbs)	7.0 +/- 0.2

TUC1378 is a crosslinker for TUC1402 air-dry stain-resistant topcoat. Solution is crosslinked by blending under agitation 98.2%/1.8% (TUC1396R/TUC1397R). The crosslinked solution is applied on boat bottom and cures at room temperature after 24 hours. Check stain with black permanent marker - must clean completely with 100% IPA.

