

TUC1396R Dull TPO Automotive Primer

TECHNICAL DATA SHEET

Technical Specifications	TUC1396R
% Solids	15.0 +/- 1.0
Viscosity	12.0 +/- 1.0 seconds #3 Zahn
Weight per Gallon (lbs)	7.5 +/- 0.2
Grind	7+
Solvent System	MEK/ Toluene

TUC1396R Dull TPO Primer is used in automotive type applications and has been used in this application by some of the major TPO manufacturers for more than 20 years. It can be used with TUC1397R crosslinker. This primer has excellent adhesive properties that aid in recoating topcoats.

TUC1396R can be crosslinked with TUC1397R by blending under agitation 98.2%/1.8% (TUC1396R/TUC1397R). Once crosslinked, this solution has a 24hour pot life.

Crosslinked primer can be coated using a 120Quad roller.