

# TUC1397R Crosslinker for Solvent TPO Primer

## TECHNICAL DATA SHEET

Technical Specifications	TUC1397R
% Solids	100
Viscosity	1200.0 +/- 200.0 mPa·s
Weight per Gallon (lbs)	9.45 +/- 1.0

TUC1397R is a crosslinker for TUC1396R Dull TPO Primer. Solution can be crosslinked by blending under agitation 98.2%/1.8% (TUC1396R/TUC1397R). Once crosslinked, this solution has a 24hour pot life. Crosslinked primer can be coated using a 120Quad roller.