

TUC1398R Dull PU Non-Burnishing Topcoat for PVC/TPO

TECHNICAL DATA SHEET

Technical Specifications	TUC1398R
% Solids	18.0 +/- 2.0
Viscosity	23.0 +/- 5.0 seconds #3 Zahn
Weight per Gallon (lbs)	7.5 +/- 0.2
Grind	7+
Gloss	1.5 +/- 0.1

TUC1398R dull PU non-burnish topcoat is used in automotive type applications and has been used in this application by some of the major TPO and PVC manufacturers for more than 20 years. It passed automotive burnish test, along with all other abrasion, elongation, and light/heat stability tests required.