

TUC1402 Air Dry SRT for Boat Bottom

TECHNICAL DATA SHEET

Technical Specifications	TUC1402
% Solids	32.0 +/- 2.0
Viscosity	13.0 +/- 2.0 seconds #3 Zahn
Weight per Gallon (lbs)	7.7 +/- 0.2
Grind	7+

TUC1402 is an air-dry stain-resistant topcoat for boat bottom application. TUC1402 is crosslinked with TUC1378 by blending under agitation 86%/14% (TUC1402/TUC1378). The crosslinked solution is applied on fiber glass and cures at room temperature after 24 hours. Check stain with black permanent marker - must clean completely with 100% IPA.

