

TUC1404 Dull SRT - Solvent Stain Resistant Topcoat

TUC1405 Gloss SRT - Solvent Stain Resistant Topcoat

TECHNICAL DATA SHEET

Technical Specifications	TUC1404 Dull	TUC1405 Gloss
% Solids	32.5 +/- 2.0	33.0 +/- 3.0
Viscosity	13.0 +/- 1.0 seconds #3 Zahn	11.0 +/- 3.0 seconds #3 Zahn
Weight per Gallon (lbs)	7.8 +/- 0.2	7.7 +/- 0.2
Grind	7+	7+
Solvent System Stain Test (All clean with 100% IPA wipes)	<ul style="list-style-type: none"> • Black & Red permanent marker cleans w/ 100% IPA • Coffee cleans w/ soap & water 	<ul style="list-style-type: none"> • Black & Red permanent marker cleans w/ 100% IPA • Coffee cleans w/ soap & water

Stain Test (over TUC1412 & TUC1386 Dull PU Primers): TUC1404 is a dull solvent based pre-crosslinked topcoat, that needs to attain the equivalent of 150°C for 1 minute. It can be applied with a 95Quad roller. Check stain with black permanent marker - must clean completely with 70% IPA.

TUC1404 can be blended with TUC1405 to achieve adequate gloss. This coating is stable and does not need to be re-crosslinked over time. It will not gel or lose properties if fully mixed under agitation and the viscosity is maintained between 12-14 seconds #3 Zahn. When finished with a run, drain the pan, adjust the viscosity with IPA and store the remainder in a sealed drum until needed again.

