

TUC2012 Crosslinker for Water Based Non-Burnishing Topcoat

TECHNICAL DATA SHEET

| Technical Specifications | TUC2012 |
|--------------------------|------------------------------|
| % Solids | 43.0 +/- 2.0 |
| Viscosity | 13.0 +/- 1.0 seconds #3 Zahn |
| Weight per Gallon (lbs) | 8.7 +/- 0.2 |
| Grind | 7+ |

TUC 2012 is a carbodiimide crosslinker for water based non-burnishing topcoat. This crosslinker is used in conjunction with TUC 2020 and TUC 2020-1 by blending under agitation 95.0%/5.0% (TUC2020-1/TUC2012). Once crosslinked, the viscosity should be 16-20 seconds #3 Zahn and will not gel.