

# High Performance Solvent Inks

## AUTOMOTIVE GRADE SOLVENT INKS

Color	Product Code	Description	C.I.	Wt/Gal	Viscosity
Blue	TIB393R	P. Blue G/S Ink	Pigment Blue 15:3 (74160)	8.2 +/- 0.2	500 +/- 250 CPS #4 Spindle 20 RPM
	TIB396	P. Blue R/S Ink	Pigment Blue 15:2 (74160:2)	8.0 +/- 0.2	1,000 +/- 500 CPS #4 Spindle 20 RPM
	TIB407	Indo Blue R/S Ink	Pigment Blue 60 (69800)	7.9 +/- 0.2	15.0 +/- 3.0 seconds #3 Zahn
Green	TIG549R	P. Green B/S Ink	Pigment Green 7 (74260)	8.5 +/- 0.2	500 +/- 250 CPS #4 Spindle 20 RPM
Black	TIK814R	Carbon Black Ink	Pigment Black 7 (77266)	7.6 +/- 0.2	250 +/- 150 CPS #4 Spindle 20 RPM
	TIK860	Jet Black Ink	Pigment Black 7	7.8 +/- 0.2	175 +/- 75 CPS #4 Spindle 20 RPM
Orange	TIO36R	Indo Orange Ink	Pigment Orange 43 (71105)	7.6 +/- 0.2	1,000 +/- 500 CPS #4 Spindle 20 RPM
Red	TIR819	Red B/S Ink	Pigment Red 254	7.4 +/- 0.2	16.0 +/- 2.0 seconds #3 Zahn
	TIR862R	Red Oxide Ink	Pigment Red 101 (77491)	10.8 +/- 0.5	1,500 +/- 500 CPS #4 Spindle 20 RPM
	TIR869	Quin Red Y/S Ink	Pigment Violet 19	7.7 +/- 0.3	450 +/- 350 CPS #4 Spindle 20 RPM
	TIR890	Quin Red B/S Ink	Pigment Violet 19	8.0 +/- 0.3	2,300 +/- 300 CPS #4 Spindle 20 RPM
Violet	TIV944M	Carbazole Violet Ink	Pigment Violet 23	8.0 +/- 0.3	300 +/- 100 CPS #4 Spindle 20 RPM
	TIV945R	Quin Violet B/S Ink	Pigment Violet 19 (73900)	8.4 +/- 0.5	700 +/- 200 CPS #4 Spindle 20 RPM
White	TIW217	White Ink	Pigment White 6 (77891)	12.1 +/- 0.3	5,000 +/- 1,000 CPS #4 Spindle 20 RPM
Yellow	TIY260	Quin Yellow Ink	Pigment Yellow 138 (56300)	7.6 +/- 0.2	600 +/- 400 CPS #4 Spindle 20 RPM
	TIY288	Irgazin Yellow Ink	Pigment Yellow 110	8.5 +/- 0.2	5,000 +/- 1,500 CPS #4 Spindle 20 RPM
	TIY289R	Yellow Oxide Ink	Pigment Yellow 42	10.5 +/- 0.2	2,500 +/- 1,500 CPS #4 Spindle 20 RPM
Metallic	TIM1011	Metallic Urethayne		7.9 +/- 0.1	